

Sammenligningstabell over aktuelle glasstyper

nov.04

	Pilkington	U/LT/TST	St. Gobain	U/LT/TST	Glaverbel	U/LT/TST	Euroglass	U/LT/TST
Nøytrale Lys og					Stopray Energy	1,1/71/39	CN 70/40	1,1/70/40
varmeregerende glass	Suncool HP Nøytral	1,4/55/40	Cool-lite KN 155	1,3/49/36	Stopray Nøytral	1,1/50/42	CN 50/37	1,1/50/37
	Suncool HP Clear	1,1/65/42	Cool-lite KN 169	1,2/62/42	Stopray Cristal	1,1/61/40	CN 62/45	1,1/62/45
			Cool-lite SKN 172	1,1/66/38	Stopray Elite	1,1/67/37		
	Brilliant 66	1,0/66/34	Cool-lite SKN 165B	1,1/58/30	Stopray Safir	1,1/61/32	CN 61/32	1,0/61/32
	Brilliant 50	1,0/50/25	Cool-lite SKN 154	1,1/50/25	Stopray Carat	1,1/52/26	CN 50/25	1,1/50/25
Reflekterende glass	Suncool HP Silver	1,1/45/28	Cool-lite KS 147	1,1/44/28	Stopray Sølv	1,1/43/27	CS 43/27	1,1/43/27
Energiruter	Optitherm SN	1,1/80/63	Planitherm Futur N	1,1/79/61	Top N	1/79/64	SST 1,1 N	1,1/79/63

Verdiene er angitt for glasskombinasjonen 6-15-6, unntatt for Energiruter som er 4-15-4.

Alle u-verdier er ISO-verdier i Argonfylte ruter, d.v.s. sentermålte verdier uten randsonetap. Tst i % =SF eller g som desimaltall